

UV85H UV Resin

UV Resin 85H is a 1-part resin high-quality, slow-viscosity synthetic resin. The resin can be easily applied to the desired surface or mold, and then exposed to UV light or direct sunlight for curing. The resin is durable, waterproof, and resistant to yellowing and scratching, ensuring long-lasting creations. It's also self-leveling which reduces the need for post-curing finishing.

This crystal-clear resin is perfect for various crafts and DIY projects, including jewelry making, encapsulating objects, and small item casting. It offers a fast curing time of 2-4 minutes under UV light, and it's compatible with a variety of molds, pigments, and additives making. It can be used as an adhesive to bond items with high permeability, such as glass decoration, crystal technology, crystal word, etc. It's a favorite among beginners and professionals.

TECHNICAL OVERVIEW

Physical Properties	Thin	Medium	Thick
Viscosity	1500cps	2000cps	12000cps
Color	Clear	Clear	Clear
Shore D Hardness	85D	85D	85D
Cure Time	120s	120s	60s
Full Cure	12h	12h	12h

These tests were conducted at 77°F/25°C

Customizable

- Curing time: Fast Cure/Slow Cure
- OEM Packaging
- viscosity
- It can be matched with tools (measuring cups, molds, stirring rods, etc.) to customize the set.











Rapid curing

HigherRefractiveIndex

Crystal Clear

Anti-yellowing

anti-scratched

UV Lamp Parameters

UV Lamp Parameters				
Power	1kw			
Wavelength	365nm~395nm			
Irradiation Distance	2cm			
Irradiation Time	120s			
These tests were c	onducted at 77°F/25°C.			
Pot life and tack-free time can v	ary depending on volume and room			

UV Lamp Parameters				
Power	18w			
Wavelength	365nm~395nm			
Irradiation Distance	2cm			
Irradiation Time	120s			
These tests were conducted at 77°F/25°C.				
Pot life and tack-free time can va-	ry depending on volume and room			

UV Lam	p Parameters			
Power		8W		
Wavelength	3	365nm~395nm		
Irradiation Distance		2cm		
Irradiation Time	120s	120s	60s	
These tests were	conducted at 7	7°F/25°C.		
Pot life and tack-free time can va	ry depending o	n volume and	room tem	



















86 186 7596 2532



www.diyresins.com



DIYRESINS



sales02@diyresins.com



Room 801, Building 1, Phase III Zhongheng International Commercial Plaza No.173 Yingbin Avenue Huadu District, Guangzhou City